arXiv:1609.04450v1 [cond-mat.mes-hall] 14 Sep 2016

An Introduction to Graphene Plasmonics

Paulo André D. Gonçalves
Nuno M. R. Peres

Publishers' page

Publishers' page

Publishers' page

Publishers' page

To our families:
(Inês and João Nuno, and Augusta, Augusto, and Filipa)

And our parents:
(*Clementina and João Paulo, and Cecília and Luís*)



Foreword

The consequences of plasmons, collective excitations of the electron plasma in conductive materials, have been appreciated for centuries — if not millenia, just witness the beautiful ancient colored glasses which are found in museums and churches. There, the colors originate from localized surface plasmonic excitations in nanoscale metallic particles. This old example crystallizes the essence of modern plasmonics: on one hand, one needs surfaces, and on the other hand the active objects should be in the nanometer scale. Graphene, the wonder material of the 21st century, is two-dimensional and therefore all surface; it is just one atomic layer thick and by using modern nanofabrication technologies it can be sculpted laterally to nanoribbons or nanoflakes. Graphene has very special optical properties, which stem from its fascinating Dirac-like electronic dispersion law its charge carriers obey. It is no wonder then that graphene plasmonics is an important and growing area of research. Most importantly, it holds the promise of many practical applications, for example in plasmonic circuitry, nanophotonics, and sensing, just to mention a few.

This is a book on graphene plasmonics. It originates from a group that is world-known for its research in this area — who would be better qualified to write such a book? Students entering graphene plasmonics have had a difficult time in navigating between original research articles, which rarely are particularly pedagogical in their approach, and text books addressing plasmonics (many of which are excellent), but usually having conventional metals as the working material. The present book thus fills in an important gap. Now, all the relevant material is collected in a single volume. What is essential is that the material is thoroughly worked through: the approach is extremely systematic, all equations follow from previous equations in a manner that a dedicated student can easily follow. The technical

level of the book is accessible to an advanced undergraduate or a beginning graduate student, but experienced researchers will also benefit from the many insights it offers. It starts with an introduction to Maxwell's equations, and thereafter works its way towards graphene, and the nanostructures made of graphene. The very important issue of interfaces and two-dimensionality is given an exhaustive treatment. Underway the quantum mechanical description of graphene's electronic structure is developed, including effects due to applied magnetic fields, and central topics in many-body physics are discussed (and further explained and elaborated in useful appendices). With the basic concepts at hand, the reader is taken to the frontier of today's research: plasmons in nanostructured two-dimensional materials, such as arrays of microribbons, nanorings, and gratings. The excitation mechanisms needed to launch plasmons and plasmon-polaritons are discussed, as well as methods that are required to observe the excited plasmons. The authors should be congratulated for having accomplished an important task: to offer a self-contained and complete, yet accessible, treatment of a modern area under rapid progress. Armed with the knowledge extracted from this book tomorrow's students are ready to tackle the many exciting opportunities and challenges that plasmonics in two-dimensional materials offer.

Antti-Pekka Jauho,
Technical University of Denmark,
2016

Preface

Over the last few years, graphene plasmonics has emerged as a new research topic, positioned at the interface between condensed matter physics and photonics. This still young but rapidly growing field, resulting from the overlap between graphene physics and plasmonics, deals with the investigation and exploration of graphene surface plasmon-polaritons (GSPs) for controlling light-matter interactions and manipulating light at the nanoscale.

In 2011, experimental research in plasmonics in graphene was in its infancy. Some theoretical papers had already been written, but the field was awaiting for some sort of experimental boost. In 2011 a seminal experimental paper (to be discussed in Section **??**) emerged, demonstrating that plasmonic effects in graphene could be controlled optically, by shining electromagnetic radiation onto a periodic grid of graphene micro-ribbons. This opened a new avenue in graphene physics, launching the new flourishing field of graphene plasmonics. Since then, the field has been witnessing enormous developments at a rapid pace (to be described in Section 1.2).

This is a book on plasmonics in graphene. It grew out of the authors' own interest in the field. Many of the topics covered here refer to problems that were amongst the first to appear in the scientific literature, to which one of the authors has contributed to some extent. Throughout this monograph we have tried to make this book as self-contained as possible, and to provide substantial detail in all derivations. Indeed, with a pencil, some sheets of paper, a dose of enthusiasm, and, at times, a bit of effort, the interested reader should find it easy to reproduce all the results in the book (the Appendices will be most useful for such endeavor). Therefore, we hope that this book will serve as a springboard for any newcomer in graphene

plasmonics. Hopefully, the advanced researcher may also find reasons to keep this book in her/his shelf and to recommend it to her/his students. This is also a book about theoretical techniques to deal with plasmonics in graphene. Many of these techniques have been applied to metal plasmonics before and have been adapted here to tackle plasmonic effects in graphene. The main difference is that metals are described by a complex dielectric function, whereas graphene is described by its complex (non-local whenever necessary) optical conductivity and its sheet (two-dimensional) current.

The book is organized as follows: in Chapter 1 we introduce the theme of the book and present a short review of the literature. We have surely missed some important references and can only hope for the indulgence and comprehension of their authors. This might be specially true in what concerns theoretical and computational work (the literature is already too vast to be covered in a comprehensive way). In Chapter **??** we review some elementary concepts about electronic transport in solids, give a short introduction to graphene's electronic properties, and present some tools to be used later in the book, with particular emphasis on a method to compute the non-local optical conductivity of graphene from the electronic susceptibility in the relaxation-time approximation. Chapter **??** discusses plasmonics at metal-dielectric interfaces and in metal thin films. The results obtained there will be later compared with those found in graphene. Both the semi-infinite metal and the thin metal-film are discussed. In Chapter **??**, we finally dive into the field of graphene plasmonics and discuss plasmons both in single- and double-layer graphene. The interesting problem of coupled surface plasmon-phonon-polaritons is also discussed in that Chapter. A short introduction of magneto surface plasmon-polaritons is included, considering both the semi-classical and quantum regimes. We close the chapter with the study of guided (bounded) surface phonon-polaritons in a crystal slab of hexagonal boron-nitride (hBN), a problem very recently considered in the literature and one for which many future developments are expected.

As we shall see, surface plasmons cannot be directly excited in graphene by free propagating electromagnetic waves (as is also the case in planar metal-dielectric interfaces). Thus, in Chapter **??** we review some of the most popular methods of inducing surface plasmon-polaritons in this two-dimensional material (which are also used in traditional metal-based plasmonics). We then move to a detailed study of two methods for exciting plasmons in graphene. These are discussed in Chapters **??** and **??**, encom-

passing the excitation of GSPs by a metallic antenna and by coupling light to GSPs in a patterned array of graphene ribbons. The discussion of the periodic graphene ribbons system sets the stage for the discussion of the spectrum of surface plasmons in graphene micro-ribbons, micro-rings, and disks. This is done in Chapter **??**, where the case of a micro-deformation of the graphene sheet is also discussed, taking as an example the problem of a Gaussian groove. This latter case can be considered an example of nano-structured graphene. These three problems are considered in the electrostatic limit, which turns out to be a rather good approximation when dealing with plasmons in graphene. As we shall show they exhibit scale invariance, a property of the electrostatic limit. It then follows, in Chapter **??**, a discussion of the excitation of plasmons by a corrugated dielectric grating, which is a generalization of the single micro-deformation studied in the preceding chapter to the case of a periodic deformation. In this case, the calculation takes retardation into account, but could very well be treated within the electrostatic approximation. Despite some differences, the four methods discussed in Chapters **??**, **??**, **??**, and **??** have in common the decomposition of the fields in a superposition of Fourier modes, either using a Fourier series, for periodic structures, or a Fourier integral for non-periodic systems. In Chapter **??** we discuss how an emitting dipole (for example, a dye, a quantum dot, or a Rydberg atom) can excite graphene plasmons by non-radiative energy transfer from the emitter to graphene. We will see that this is in principle possible, and we compute the non-radiative decaying rate of an emitter. The role of particle-hole processes and excitation of plasmons is discussed separately. We end this Chapter with the calculation of the Purcell factor which encodes information about the total decaying rate of the emitter in the presence of graphene. Finally, in Chapter 2, we conclude with a brief outlook and with the discussion of some topics that have been left out in this book, and which we believe will become rather important in the near future. Also, we have written a number of appendices with either details of the calculations or extensions of the materials discussed in the bulk of the book. To get a flavor of the main ideas, reading the appendices is unnecessary. However, they are a requisite for a working knowledge on the topics discussed in the main text.

Our ultimate hope is that readers may find this book a valuable tool for their study and research in the exciting field of graphene plasmonics and nanophotonics, whether they are currently working on the topic or are about to enter on it. The book's intended purpose is to bring together some of the main topics that are scattered throughout the already vast

literature, and to do justice to this alluring field of graphene plasmonics.

To conclude, we further hope that the readers may read this book with the same enthusiasm that we had writing it. Comments, suggestions, and corrections aiming at improving the book for future usage will be most welcome (these can be sent to peres@fisica.uminho.pt).

Paulo André Dias Gonçalves
Nuno Miguel Machado Reis Peres

Department of Physics
University of Minho
Braga, 2016



Acknowledgments

The authors acknowledge B. Amorim, Y. V. Bludov, E. V. Castro, A. H. Castro Neto, A. Chaves, A. Ferreira, F. Guinea, J. Lopes dos Santos, V. Pereira, R. M. Ribeiro, J. E. Santos, T. Stauber, and M. I. Vasilevskiy for many years of collaboration and discussions about the physics of graphene in general and on plasmonics in graphene and other materials in particular. We thank B. Amorim, Y. V. Bludov, A. Chaves, A. Ferreira, J. Lopes dos Santos, R. M. Ribeiro, J. E. Santos, and M. I. Vasilevskiy for reading parts of the manuscript at different moments of writing. B. Amorim is acknowledged for providing the derivations in Appendices **??**, **??**, and **??**. A. Chaves is acknowledged for providing the derivation in Appendix **??** J. E. Santos is acknowledged for providing the derivation in Appendix **??**. Any error and/or inaccuracy that may remain in the text of these five Appendices (and, for that matter, in the rest of the text) is the authors' own responsibility.

Paulo André Gonçalves acknowledges the Calouste Gulbenkian Foundation for financial support through the grant "*Prémio Estímulo à Investigação 2013*"[1] (No. 132394) and the hospitality of the Centre of Physics of the University of Minho, where most of this book was written. Nuno Peres acknowledges financial support from the Graphene Flagship Project (Contract No. CNECT-ICT-604391).

[1] "Gulbenkian Prize for Stimulating Young Researchers 2013".



Contents

Foreword vii

Preface ix

Acknowledgments xv

List of Figures xix

List of Tables xxi

1. Introduction 1

    1.1 Plasmonics: Generalities 1
    1.2 Plasmonics: Recent Developments 4

2. Concluding Remarks 11

Bibliography 17



List of Figures



List of Tables



Chapter 1

Introduction

Plasmonics holds many promises [Atwater (2007)], such as plasmonic integrated circuitry [Sorger *et al.* (2012)], nanophotonics (e.g., plasmonic antennas) [Dionne and Atwater (2012)], all-optical manipulation of small particles [Quidant (2012)], quantum plasmonics [Jacob (2012); Hanson *et al.* (2015)], spin-polarized plasmonics [Toropov and Shubina (2015)], and plasmonic hot-spots [Weber and Willets (2012)], just to name a few. Whether graphene will be able to fulfil some of these promises remains to be seen, but current prospects are encouraging. This book is about plasmonics in graphene and about the methods to excite and control surface plasmons in this material. Below, we give a brief account of some of the recent developments in the field.

1.1 Plasmonics: Generalities

The recent burst of interest in plasmonics may overshadow the fact that plasmon-related effects can be traced back to the turn of the twentieth century with the works of A. Sommerfeld and J. Zenneck on the propagation of electromagnetic waves along the surface of a conductor [Sommerfeld (1899); Zenneck (1907)]. Concurrently, in 1902, R. H. Wood reported the observation of anomalous intensity drops in the spectrum of visible light diffracted by a metallic grating, which became known as Wood's anomalies [Wood (1902)]. However, Wood was unable to develop any suitable interpretation for this phenomenon. The first effort towards a theoretical interpretation of Wood's results was conducted by Lord Rayleigh [Rayleigh (1907)], albeit with limited success, and was followed by the works of Fano a few decades later [Fano (1941)]. Fano's work was subsequently improved by many [Enoch and Bonod (2012)]. Some of these breakthroughs took

place during the 1950s and 1960s [Hessel and Oliner (1965); Ritchie *et al.* (1968)], along with the development of the concept of *surface plasmon-polariton* and its excitation both via the use fast electrons [Powell and Swan (1959); Ritchie (1957)] and through prism coupling[1] [Kretschmann and Raether (1968); Otto (1968); Sambles *et al.* (1991)] (see [Gupta *et al.* (2015)] for an historical perspective on plasmonics).

Surface plasmon-polaritons (SPPs) are electromagnetic surface waves coupled to collective charge excitations of the conduction electrons, propagating along the interface between a dielectric and a conductor. When these coupled excitations occur in metallic nanostructures —such as nanoparticles (NPs)—, the corresponding non-propagating plasmon-polaritons are generally coined as localized surface plasmons (LSPs) [Pelton *et al.* (2008); Pelton and Bryant (2013); Stockman (2011)].

Notwithstanding, modern plasmonics as we know it emerged in the turn of the 21st century with the observation by T. W. Ebbesen *et al.* of an "extraordinary optical transmission through subwavelength hole arrays" in a periodically patterned metal film [Ebbesen *et al.* (1998)]. Shortly after this seminal paper, a theoretical account of this experiment was developed invoking the role SPPs [Martín-Moreno *et al.* (2001)]. One notable feature of SPPs modes is that their momentum is larger than light's momentum corresponding to photons with the same frequency [Maier (2007)]. As a consequence, SPPs are bound modes whose fields decay exponentially away from the interface, exhibiting subwavelength confinement [Barnes *et al.* (2003)] and field enhancement (which can be of several orders of magnitude larger than the value of the incident field) beyond the reach of conventional optics [Barnes *et al.* (2003); Barnes (2006); Maier (2007)]. Thus, plasmonics opened up the possibility for manipulating light and control light-matter interactions at scales well below the diffraction limit (and at the nanoscale), being one of the most promising research topics in the field of nanophotonics and also an important ingredient in the design and implementation of metamaterials [Kabashin *et al.* (2009); Liua and Zhang (2011); Billings (2013)].

Nowadays, plasmonics plays a leading role towards the miniaturization

[1]Otto and Kretschmann-Raether are often considered as the first to excite SPPs in metal thin films using a prism. The fact, however, is that Turbadar was the first to excite surface plasmon-polaritons in aluminium (and later in silver and gold) thin films using the prism coupling method [Turbadar (1959)]. However, and contrary to Otto and Kretschmann-Raether, he did not correlated the minimum in the reflectance with the excitation of SPPs.

of photonic structures and circuitry [Ebbesen *et al.* (2008)], along with their integration with current semiconductor technologies [Ozbay (2006)]. For telecommunications and/or information processing photonics offers high speeds and large bandwidths, but albeit at a cost, since bulky components —at least in comparison to chip-based nanoelectrics— are the rule; on the other hand, although electronics provides the much-wanted miniaturization and good carrying capacities, its ability to deal with huge amounts of information is limited by the number of connections, resulting in transmission bottlenecks. Therefore, the hybrid nature of SPPs (being "half-light, half-matter" bosonic quasiparticles, i.e. polaritons) makes them an attractive route to close the gap between photonic and electronic circuits, by combining the advantages of both "worlds".

The revival of the field over the past decade was, to a large extent, due to a rapid development of nanoscale fabrication techniques and experimental tools, together with the implementation of powerful numerical modelling based on full-wave electromagnetic simulations. These triggered the emergence of a plethora of exciting applications (which are often strong motivators by themselves), such as spectroscopy and biochemical sensing [Anker *et al.* (2008); Kabashin *et al.* (2009); Brolo (2012); Haes *et al.* (2005)], optical tweezers [Reece (2008); Juan *et al.* (2011)], photovoltaics and energy harvesting [Green and Pillai (2012); Boriskina *et al.* (2013)], diagnostics and nanomedicine [Aćimović *et al.* (2014); Zheng *et al.* (2012); Vo-Dinh *et al.* (2013)], SPP-based amplifiers and lasers [Berini and Leon (2012); Ma *et al.* (2013)], Fourier and transformation optics [Archambault *et al.* (2009); Huidobro *et al.* (2010); Zhang *et al.* (2011)], etc. Yet, the field of plasmonics is far from being exhausted and continues to thrive. Recently, special attention has been given to forefront research themes including ultrafast plasmonics [MacDonald *et al.* (2009)], non-linear phenomena with SPPs [Kauranen and Zayats (2012)] and quantum plasmonics [Tame *et al.* (2013); van Hulst (2012); Jacob (2012)]. This latter field studies the quantum properties of SPPs, setting up novel ways to investigate new fundamental physics and to fuel the prospection for plasmonic devices operating in the quantum regime [Jacob and Shalaev (2011); Chang *et al.* (2006)]. Several quantum optics experiments with SPPs have been reported [Heeres *et al.* (2013); Fakonas *et al.* (2014); Di Martino *et al.* (2014); Cai *et al.* (2014)], demonstrating the maintenance of quantum coherence and unitarity in (quantum) photonic systems, despite the macroscopic, collective nature (encompassing $\sim 10^6$ electrons) of SPPs [Tame *et al.* (2013)]. New frontiers in metal-semiconductor plasmonics are discussed in [Toropov

and Shubina (2015)] and a modern introduction to plasmonics is given in [Maradudin *et al.* (2014)]. The interested reader in localized surface plasmons may want to check [Klimov (2014)].

1.2 Plasmonics: Recent Developments

In the present book we are concerned with graphene as a plasmonic material —graphene plasmonics [Bludov *et al.* (2013); Grigorenko *et al.* (2012); Low and Avouris (2014); de Abajo (2014); Luo *et al.* (2013); Koppens *et al.* (2011); Stauber (2014)]. Isolated in 2004 [Novoselov *et al.* (2004)], graphene —a two-dimensional (2D) crystal made up of carbon atoms arranged in a honeycomb lattice— has been, in the last decade, one of the hottest topics in condensed matter physics, owing to its remarkable electronic, mechanical, and optical properties [Geim (2009); Castro Neto *et al.* (2009)]. As in the case of plasmonics, the number of publications on graphene physics has escalated during the past decade. However, the two fields have evolved quite independently up until very recent times. In fact, the bridge between both these subjects was well-established only as recently as in 2011, motivated by the experimental realization of graphene surface plasmon-polaritons (GSPs) in periodic arrays of graphene ribbons, obtained by patterning a pristine graphene sheet [Ju *et al.* (2011)]. This foundational work has sparked a whole interest in graphene nanoplasmonics, setting the stage for the investigation of graphene as a novel plasmonic material.

Doped graphene is capable of sustaining SPPs [Jablan *et al.* (2009); Bludov *et al.* (2013); Jablan *et al.* (2013); Ju *et al.* (2011); Yan *et al.* (2013); Strait *et al.* (2013); de Abajo (2014); Christensen *et al.* (2012)], which can be actively controlled and tuned through chemical doping or electrical gating, almost in real time. This contrasts with conventional metal-based plasmonics [Toropov and Shubina (2015)], where the tunability is usually limited— it can be only achieved, essentially, by controlling the size, the shape, and the dielectric environment of metallic nanoparticles (the polarization of the electric field also plays a role), the geometry of metal-based nanostructures, or by exploring the thickness of thin films of noble-metals. Furthermore, graphene surface plasmon-polaritons enable higher levels of spatial confinement (within volumes of the order of $\sim \alpha^{-3} \approx 10^6$ below the diffraction limit; here α is the fine structure constant of atomic physics) and are predicted to suffer from relatively low losses[2], therefore having larger lifetimes

[2]See [Yan *et al.* (2013)] for a discussion of the damping channels of plasmons in graphene

and propagation lengths, when compared with traditional plasmonic materials. This makes graphene an appealing candidate for nanoplasmonic and nanophotonic applications. The spectral region of graphene plasmonics has been restricted to the terahertz (THz) and mid-infrared (mid-IR), a region that traditional metal-based plasmonics cannot cover, since the SPP's in a continuous metallic film are essentially free radiation at such frequencies, therefore lacking a key advantage of SPP's in graphene, the strong spatial confinement.

As is well known, the electrons in graphene are described by a massless Dirac equation, contrary to the 2D electron gas. The spectrum of SPPs' in graphene provides an indirect confirmation of the form of the dispersion of electrons in this material. Although the frequency of GSPs scales with momentum as $\sqrt{q}$ like in the classic 2DEGs (two-dimensional electron gases), the GSP frequency is proportional to the electronic density as $n_e^{1/4}$, which is specific of graphene (for 2DEG, a $n_e^{1/2}$ scaling is observed instead). This is a direct consequence of the unique electronic properties of graphene, whose electrons behave like relativistic Dirac fermions with a linear dispersion [Castro Neto *et al.* (2009)] (this is true at low energies, that is, in the vicinity of the Dirac points). Another peculiarity of graphene is its ability to support transverse electric[3] (TE) modes [Mikhailov and Ziegler (2007)], which do not occur in ordinary metal/dielectric structures [Maier (2007)].

The frequencies of transverse magnetic (TM) GSP typically lie between the THz and mid-IR regions of the electromagnetic spectrum. While the THz spectral region remains relatively unexplored, THz photonics has become an active field of research over the last few years [Mittleman (2013)]. Here too, graphene plasmonics may contribute to the development of this subject [Tassin *et al.* (2013); Low and Avouris (2014)]. For instance, a geometry akin to the one described in [Ju *et al.* (2011)] together with subwavelength bimetallic electrodes has recently been engineered to achieve plasmon-enhanced THz photodetection using graphene [Cai *et al.* (2015)].

Having passed its infancy, one may state that graphene plasmonics is

nanostructures; see [Khurgin and Boltasseva (2012)] for a discussion of the same topic in metal-based plasmonics and metamaterials as well as their possible replacement by conducting oxides and transition metal nitrides

[3]We bring to the reader's attention that, up to this point, whenever we mentioned SPP/GSP it was implicit that we were referring to transverse magnetic modes. This will also be the case throughout the rest of the book, unless explicitly stated otherwise.

now entering its young adult life (in fact, it is maturing rather fast). Yet, during these early stages of the field, there were already some remarkable achievements that took place which might be worth mentioning. Apart from the above-referenced excitation of GSPs in periodic gratings made up of graphene stripes [Ju *et al.* (2011); Strait *et al.* (2013); Yan *et al.* (2013); Nene *et al.* (2014)], other experimental landscapes for coupling light to GSPs were also explored, ranging from graphene disks [Fang *et al.* (2013, 2014); Yan *et al.* (2012c)], dimers [Christensen *et al.* (2012); Thongrattanasiri and de Abajo (2013)], resonators [Brar *et al.* (2013, 2014)], rings [Fang *et al.* (2013); Yan *et al.* (2012c)], periodic dot/anti-dot lattices [Yan *et al.* (2012a); Fang *et al.* (2013, 2014); Liu *et al.* (2015b); Yan *et al.* (2012c); Zhu *et al.* (2014)], stacks of graphene disks/ribbons [Yan *et al.* (2012a,c)], periodically modulated or corrugated graphene [Peres *et al.* (2012); Slipchenko *et al.* (2013)], continuous monolayer graphene resting in dielectric gratings [Gao *et al.* (2013); Zhu *et al.* (2013c); Gao *et al.* (2013)], nano-antennas [Liu *et al.* (2014); Llatser *et al.* (2012); Yao *et al.* (2013); Fang *et al.* (2012a,b); Alonso-González *et al.* (2014)], among others [Koch *et al.* (2010); Fei *et al.* (2011, 2012); Chen *et al.* (2012)]. Moreover, the unique tunability of GSPs was demonstrated in these experiments, through the shifts of plasmon resonances in response to changes in the amount of doping induced via electrical gating. Indeed, this enables high-speed electro-optical modulation by taking advantage of the capability of significantly (and quickly) alter graphene's optical properties using electric gates [Sensale-Rodriguez *et al.* (2012); Lee *et al.* (2012); Li *et al.* (2008)]. Also, the complete absorption of light in periodic arrays of doped graphene nanodisks, which may have strong implications in photovoltaics and light harvesting platforms, has been predicted in a theoretical work [Thongrattanasiri *et al.* (2012a)]. This constitutes a truly astonishing result taking into account that this is a one-atom-thick material.

A particularly tantalizing and very application-oriented approach, involves the use of GSPs to grant us graphene with bio and chemical sensing capabilities [Wu *et al.* (2010); Vasić *et al.* (2013); Zhao *et al.* (2013); Zhang *et al.* (2013); Wu *et al.* (2014a); Rodrigo *et al.* (2015)] (see also [Brolo (2012)]). The general idea behind the concept of a plasmonic sensor is to explore the subwavelength confinement and enhancement of the electromagnetic field to probe small changes in the local dielectric environment, given that the SPP/LSP resonant frequencies are highly sensitive to the optical constants of the contiguous medium [Anker *et al.* (2008)]. For instance, the adsorption of biomolecules on the surface of graphene promotes a sub-

tle modification of the effective refractive index of the sensing medium, which can be detected by measuring the corresponding spectral shifts of the plasmon resonances [Zhao *et al.* (2013)]. Here, the aim is to target graphene's potential to yield surface plasmons with superior spatial confinement and intense fields to pave the way for cutting-edge, high-performing plasmonic sensors that surpass costumary noble-metal plasmonic devices [Rodrigo *et al.* (2015)].

Another highly appraised and auspicious phenomenon is surface-enhanced Raman scattering (SERS) in plasmonic nanostructures [Kneipp (2007)]. This spectroscopic technique has been one of the most compelling applications of plasmonics, since it enables an exceptionally sensitive detection of low concentration of analytes and even label-free single molecule detection [Sharma *et al.* (2012); Crozier *et al.* (2014); Stiles *et al.* (2008); Schlücker (2014)]. In recent years, it has become popular to build hybrid SERS platforms resulting from the combination of graphene with metallic nanostructures, with the purpose of exploiting graphene's outstanding optoelectronic properties to enhance the Raman signal and also to assist the quantitative assessment of the different SERS mechanisms [Xu *et al.* (2012b); Wang *et al.* (2013)]. Graphene-mediated SERS (G-SERS) was reported in a number of experiments [Wang *et al.* (2012); Ling *et al.* (2010); Liu *et al.* (2011a); Urich *et al.* (2012); Heeg *et al.* (2013); Kravets *et al.* (2012); Zhao *et al.* (2014); Wang *et al.* (2013); Zhu *et al.* (2013b)], along with the observation of enhancement factors spanning from about 100 [Urich *et al.* (2012)] (for monolayer graphene with Ag nanoislands) or 1000 [Heeg *et al.* (2013); Kravets *et al.* (2012)] (for graphene on top of a Au nano-disk dimmer and plasmonic nanoarrays), up to values as high as 10^6 [Zhao *et al.* (2014)] and 10^{10} [Wang *et al.* (2013)] respectively for the dye molecules Rhodamine B (RhB) and Rhodamine 6G (Rh6G) in a Au-NPs/graphene/Cu composite platform, and for Rh6G and lysozyme in a bio-compatible graphene-Au nano-pyramid hybrid system.

Benefiting from the know-how acquired in the flourishing sub-branch of plasmonics dealing with metallic nanoparticles [Pelton and Bryant (2013); Garcia (2011)], the integration of plasmonic NPs with graphene has emerged as a topic worthy of attention [Fang *et al.* (2012a); Santos *et al.* (2014); Liu *et al.* (2011b); Fang *et al.* (2012b); Xu *et al.* (2012a); Yin *et al.* (2013)]. This offers new possibilities for improving the photodetection of such systems [Liu *et al.* (2011b); Fang *et al.* (2012a)], and also for enhancing the interaction between a polarizable nanoparticle and graphene [Santos *et al.* (2014)] by taking advantage of the appropriate resonances in

their spectra, together with graphene's tunability. This enhanced interaction, with its strong dependence upon the NP-graphene distance, makes this system potentially interesting for application in deformation or pressure sensors, as it is technologically feasible to control the deposition of semiconductor or metallic nanoparticles on graphene [Sun *et al.* (2011); Kamat (2010)]. In addition, shifts of surface plasmon resonances (SPRs) associated with the electromagnetic coupling between graphene and the nanoparticle(s) have been observed [Niu *et al.* (2012)], as well as changes in the SPR linewidth and plasmon-generated hot-electron transfer [Hoggard *et al.* (2013); Fang *et al.* (2012b)].

Beyond traditional noble metal NPs, another research line is connected with SPP-related physical mechanisms operating in compound systems of graphene with quasi-zero-dimensional emitters or absorbers, such as molecules or semiconductor quantum dots (QDs) [Gaudreau *et al.* (2013); Biehs and Agarwal (2013); Velizhanin and Efimov (2011); Chen *et al.* (2010)]. These architectures yield new routes to investigate the interaction among localized excitations such as molecular or QD excitons and propagating SPPs in graphene. It has been shown experimentally that graphene allows for probing the de-excitation dynamics of the emitter [Gaudreau *et al.* (2013)] and causes an enhanced Förster resonance energy transfer from a fluorescent QD [Chen *et al.* (2010)]; at the same time, a hybrid graphene–QD phototransistor with ultrahigh gain has been demonstrated [Konstantatos *et al.* (2012)]. Theoretical proposals include probing graphene-mediated control of the coupling between two emitters (Förster energy transfer [Biehs and Agarwal (2013)] and/or GSP-mediated superradiance [Huidobro *et al.* (2012)]), studies of the GSP dispersion [Velizhanin and Efimov (2011)], and enhancement of radiation absorption in graphene using nanoparticles [Liu *et al.* (2011b); Zhu *et al.* (2013a)].

All of the above has placed graphene on the map as a fertile playground for nanoscale plasmonics. Aside from the research avenues outlined in the preceding paragraphs —including the excitation and control of GSPs in a number graphene-based structures, analysis of the NPs- and QD-graphene electrodynamics, potential applications in biochemical sensing, spectroscopy, electro-optical modulation, and enhanced photodetection and optical absorption—, further developments have also been made in a variety of disciplines, encompassing transformation optics using graphene [Vakil and Engheta (2011)], graphene plasmonic metamaterials [Lee *et al.* (2012); Ju *et al.* (2011); Yan *et al.* (2012a); Ishikawa and Tanaka (2013)], atomically

thin waveguiding and optical communications [Christensen *et al.* (2012); Vakil and Engheta (2011)], cloaking devices [Chen and Alù (2011)], broadband graphene polarizers [Bao *et al.* (2011)], excitation of GSPs via surface acoustic waves [Schiefele *et al.* (2013); Farhat *et al.* (2011)], realization of magneto-plasmons in graphene [Crassee *et al.* (2012); Yan *et al.* (2012b)] (see also [Temnov (2012)]), and photothermal therapies for biomedicine [Lim *et al.* (2013)], just to name a few.

As we *begin* to unravel the fundamentals of graphene plasmonics and to take a glimpse at the physics behind graphene's strong light-matter interactions, new research frontiers are already emerging on the horizon. These include, but are not limited to, the investigation of many-body effects, namely the interaction of GSPs with other elementary excitations in graphene (such as plasmon-phonon coupling [Yan *et al.* (2013); Brar *et al.* (2014); Hwang *et al.* (2010)] and plasmarons [Carbotte *et al.* (2012)]); a better understanding of the loss mechanisms affecting GSPs' lifetimes [Yan *et al.* (2013)]; the exploration of strong-coupling regimes in graphene with single quantum emmiters [Koppens *et al.* (2011); Manjavacas *et al.* (2012b); Gullans *et al.* (2013); Cox *et al.* (2012); Manjavacas *et al.* (2012a); Tielrooij *et al.* (2015)]; studies of non-linear phenomena [Gullans *et al.* (2013); Cox and de Abajo (2014); Manzoni *et al.* (201)]; assessment of the importance of quantum finite-size effects in graphene nanostructures supporting GSPs [Thongrattanasiri *et al.* (2012b)], etc. Future perspectives also include the extension of the pioneering research conducted in graphene nanophotonics to other 2D crystals and van der Waals heterostructures (layered structures of atomically thin materials like graphene, MoS_2, WeS_2, hBN, other 2D chalcogenides, and oxides [Geim and Grigorieva (2013)]). Additional challenges are comprised with bringing graphene plasmonics towards the NIR-vis region of the electromagnetic spectrum, along with the demand of cleaner fabrication techniques. The latter are expected to deliver GSPs with lower losses while allowing a better control over the morphology and dimensions of the patterned samples. On the other hand, extreme doping, ultra-narrow graphene ribbons or disks, and nanometer-sized forms of graphene (e.g. chemically synthesized polycyclic aromatic hydrocarbons [Manjavacas *et al.* (2013)]) have been proposed [de Abajo (2014)] to carry out graphene plasmons at NIR-vis frequencies.

Although this young and vibrant field still has some demanding challenges to face, it is now beyond dispute that graphene already deserves its own place in the list of most promising plasmonic materials of the future.

Research on graphene plasmonics is intense and likely to remain one of the hottest topics in nanophotonics in the forthcoming years. In addition, the exploration of the unique properties of graphene surface plasmons may lead to a new gold rush with high impact both in fundamental science as well as in technology and industry, ultimately leading to the appearance of the next generation of devices with tailored optoelectronic properties [Yusoff (2014)].

Chapter 2

Concluding Remarks

The field of plasmonics is growing, as it can be seen from the data-plot in a recent editorial in *Nature Photonics* [Editorial (2012)]. In that article it is shown that the number of publications in plasmonics has been growing steadily over the last twenty years. Broadly speaking, we can divide the field of plasmonics according to the nature of the surface-plasmon resonances. Whenever these resonances occur in localized nano-particles we talk about localized surface plasmon-polaritons [Willets and Duyne (2007); Pelton and Bryant (2013); Klimov (2014)]. When they occur at metal/dielectric surfaces one usually denotes them as (propagating) surface plasmon-polaritons [Sarid and Challener (2010)]. In both cases, these plasmonic resonances have wavelengths below the diffraction limit [Armstrong (2012)] and exhibit intense electric fields. For propagating surface plasmon-polaritons we are generally interested in the case of propagation along a thin metal film. Since 2004 the thinnest conductive film available has been a graphene sheet. It is natural to inquire whether graphene can support propagating surface plasmon-polaritons [Low and Avouris (2014)] (which can be excited by different methods; see Chapter **??** and [Bludov *et al.* (2013); Zhang *et al.* (2014)]). Indeed, the combination of graphene and plasmonics opened a new avenue to this exciting field. This recent branch of nanophotonics is nowadays known as graphene (nano)plasmonics. For example, graphene plasmons can be used to engineer nanoscale infrared light sources [Manjavacas *et al.* (2014)], and intrinsic plasmons on graphene have already been used for enhancing photodetection [Kim *et al.* (2014); Koppens *et al.* (2014)].

Graphene, however, is not the only two-dimensional material available these days [Castro Neto and Novoselov (2011); Novoselov and Castro Neto (2012)]. Many others, as dichalcogenides (MX_2), hexagonal boron

nitride (hBN), phosphorene [Low *et al.* (2014b)], silicene, some oxides, and graphene multilayers [Low *et al.* (2014a); Wu *et al.* (2014b)], are waiting in line to be explored from the point of view of their electronic properties and light-matter interactions [Kim *et al.* (2014); Koppens *et al.* (2014)]. Indeed, a new class of materials, dubbed "van der Waals heterostructures" [Geim and Grigorieva (2013)], were conjectured to unleash a number of both new fundamental physics and new applications unforeseen until recently. On one hand, these new heterostructures [Kretinin *et al.* (2014)] can be made of two-dimensional materials (or, for that matter, of few layers of those materials); on the other hand, can be combined with more traditional materials, like noble metals [Yamaguchi *et al.* (2014); Chaves *et al.* (2014); Moriya *et al.* (2015)]. This opens a multitude of possibilities for light-matter interactions where plasmonics will certainly play a key role. Since graphene is intrinsically a surface, the coupling of surface plasmons to surface polar phonons of the underlying substrate, for instance hBN, is an interesting prospect, leading to hybrid surface phonon-plasmon polaritons [Luxmoore *et al.* (2014); Brar *et al.* (2014)], which appear as multiple dispersion branches. Furthermore, it has been shown that plasmons in graphene encapsulated in hBN possess very low damping [Woessner *et al.* (2015)]. Thus, this type of van der Waals heterostructure emerges as a plasmonic medium with high uniformity. As the field matures, low losses in plasmons propagation can be translated into long propagation lengths, which might open new routes for photonic/plasmonic-based communications and data transfer. On another topic, graphene-dichalcogenides van der Waals heterostructures, coupled to noble metals plasmonics, seem to work better as a chemical sensor than the same system in the absence of the heterostructure [Zeng *et al.* (2015)] (see also [Kravets *et al.* (2014)]); in this case, the plasmonic medium is the noble metal and not graphene, the latter acting as an intermediate for enhancing light-matter interactions. Also worth noting is the interaction of surface plasmons with grain boundaries in CVD-grown graphene. It has been shown that the reflection of plasmons at grain boundaries in graphene presents an anomalous scattering phase (different from π) [Fei *et al.* (2013); Nikitin *et al.* (2014)] (see also [Sánchez-Gil and Maradudin (1999); Polanco *et al.* (2013)] for calculations of SPPs scattering amplitudes in traditional plasmonics).

Strongly related to the field of surface plasmon-polaritons is the emerging field of surface phonon-polaritons in van der Waals heterostructures, hBN and hBN/graphene structures being the most studied. Hexagonal Boron Nitride is a hyperbolic material, that is, the in-plane and the out-

of-plane dielectric constants have different signs [Jacob (2014); Dai *et al.* (2014); Caldwell *et al.* (2014); Kumar *et al.* (2015)]. As a consequence, hBN presents two Reststrahlen bands where free radiation cannot propagate. Within these bands the system behaves like a conventional metal (as concerns radiation propagation). The existence of these Reststrahlen bands allows the propagation of surface phonon-polaritons in hBN. When graphene is deposited on hBN, an additional coupling between the surface phonon-polaritons in hBN and the surface plasmon-polaritons in graphene becomes possible, giving rise to tunable plasmon-phonon-polaritons [Dai *et al.* (2015)]. These results are opening a new field in van der Waals heterostructures.

Additionally, with the simple stacking of layered materials, a new degree of freedom enters in the game: the relative rotation of the lattices associated with different layers [Mishchenko *et al.* (2014)]. This rotation, say between a graphene layer on a boron nitride buffer layer, creates an external potential that splits the graphene bands, leading to the emergence of further plasmonic branches (dubbed spectrum reconstruction). The new avenue opened by this additional degree of freedom has not yet been fully explored [Tomadin *et al.* (2014)].

Another interesting line of research is that of plasmonics in graphene nano-structures [Christensen *et al.* (2014); Cox and de Abajo (2014); Nene *et al.* (2014); Wang *et al.* (2015); Yeung *et al.* (2014); Zhu *et al.* (2014)] or even in nanoparticles coated with graphene [Christensen *et al.* (2015)] which may also exhibit non-linear optical response [Peres *et al.* (2014); Cox and de Abajo (2015)]. In fact, the non-linear optical response of graphene has recently been used to excite surface plasmons in this material [Constant *et al.* (2015)]. Graphene's plasmonic response can also be put to good use for non-linear optics [Gullans *et al.* (2013)], and graphene itself is able to exhibit non-linear GSPs, as predicted by a recent work [Gorbach (2013)], and highly confined TE waves [Bludov *et al.* (2014)]. On a related topic, we can consider the combination of metallic nanoparticles, acting as a plasmonic material, with graphene. It has recently been shown that gold nano-disks can interact strongly with graphene, generating locally hot carriers which can be probed by femtosecond pump-probe measurements [Gilbertson *et al.* (2015)].

In this book we have only covered some aspects related to graphene plasmonics [Politano and Chiarello (2014); Low and Avouris (2014); Grigorenko *et al.* (2012); Xiao *et al.* (2016)]. We started by reviewing the basic proper-

ties of SPPs sustained at dielectric-metal interfaces, setting the stage for the discussion of SPPs in doped graphene. We then derived the dispersion relation of SPP in graphene, both in single-layer graphene and in double-layer graphene. We have seen that even for these simple geometries, the spectrum needs to be obtained by numerical means. From the corresponding solutions, it was clear that GSP-excitation is not feasible by simply striking light directly on graphene, since the dispersion curve always lies to the right of the light line. Therefore, in Chapter **??** we reviewed the most popular methods to couple electromagnetic radiation to GSPs (see also [Torre *et al.* (2015)] for a full-electrical plasmon detection method). Another interesting idea has been put forward in [Liu *et al.* (2015a)]. The excitation methods described in Chapter **??** cannot distinguish left from right propagation of plasmons. However, by putting graphene on a magneto-optical substrate, its dispersion relation becomes asymmetric in the forward and backward directions, thus allowing unidirectional excitation [Liu *et al.* (2015a)].

Motivated by a recent experiment reporting the excitation of GSPs using a metallic antenna [Alonso-González *et al.* (2014)], in Chapter **??** we have conducted a theoretical study of a similar system consisting of an infinitely long and highly conducting metal stripe placed on top of a graphene layer.

In Chapter **??** we developed a general theoretical framework for describing the excitation of GSPs in systems where the graphene's conductivity is periodically modulated. In particular, we have applied our analytical model to the case of a periodic array of graphene ribbons, since this setup has been extensively studied experimentally. We then confronted our theoretical results against the experimental data [Ju *et al.* (2011)], having observed a good agreement between theory and experiment (see also [Velizhanin (2015)]). In a recent experiment [Sorger *et al.* (2015)], GSPs' excitation in graphene stripes grown in silicon carbide has been achieved, and the same model that was used in Chapter **??** was applied to the description of the experimental data. In Chapter **??** the case of a single graphene ribbon was considered in the electrostatic limit. The approach used was then applied to graphene disks and rings. The case of a groove was also discussed. If the groove is periodically repeated we achieve a diffraction grating, a problem that can be analyzed semi-analytically. In Chapter **??** an extension of Chapter **??** was presented, which consisted of an approach to deal with graphene on periodically corrugated surfaces, that is diffraction gratings. These can be made of either a dielectric or a metamaterial, as in the case discussed at the end of that Chapter. It is worth mentioning that graphene resting on a grating can be a source of THz radiation [Zhan *et al.* (2014)],

when a beam of electrons moves over its surface, a problem that we have analysed at the end of Chapter **??** . Finally, in Chapter **??** we discussed the excitation of SPP's by an emitting dipole. We have shown that the decaying rate of a dipole is intimately tied to the excitation of SPP's on graphene, a manifestation of the Purcell effect.



Bibliography

Alonso-González, P., Nikitin, A. Y., Golmar, F., Centeno, A., Pesquera, A., Vélez, S., Chen, J., Navickaite, G., Koppens, F., Zurutuza, A., Casanova, F., Hueso, L. E., and Hillenbrand, R. (2014). Controlling graphene plasmons with resonant metal antennas and spatial conductivity patterns, *Science* **344**.

Anker, J. N., Hall, W. P., Lyandres, O., Shah, N. C., Zhao, J., and Duyn, R. P. V. (2008). Biosensing with plasmonic nanosensors, *Nature Materials* **7**, pp. 442 – 453.

Archambault, A., Teperik, T. V., Marquier, F., and Greffet, J. J. (2009). Surface plasmon fourier optics, *Phys. Rev. B* **79**, p. 195414.

Armstrong, S. (2012). Plasmonics: Diffraction-free surface waves, *Nature Photonics* **6**, p. 720.

Atwater, H. A. (2007). The promise of plasmonics, *Scientific American* **4**, pp. 1–5.

Aćimović, S. S., Ortega, M. A., Sanz, V., Berthelot, J., Garcia-Cordero, J. L., Renger, J., Maerkl, S. J., Kreuzer, M. P., and Quidant, R. (2014). Lspr chip for parallel, rapid, and sensitive detection of cancer markers in serum, *Nano Lett.* **14**, pp. 2636–2641.

Bao, Q., Zhang, H., Wang, B., Ni, Z., Lim, C. H. Y. X., Wang, Y., Tang, D. Y., and Loh, K. P. (2011). Broadband graphene polarizer, *Nature Photonics* **5**, pp. 411–415.

Barnes, W. L. (2006). Surface plasmon-polariton length scales: a route to sub-wavelength optics, *J. Opt. A: Pure Appl. Opt.* **8**, p. S87.

Barnes, W. L., Dereux, A., and Ebbesen, T. W. (2003). Surface plasmon sub-wavelength optics, *Nature* **424**, pp. 824–830.

Berini, P. and Leon, I. D. (2012). Surface plasmon-polariton amplifiers and lasers, *Nature Photonics* **6**, pp. 16–24.

Biehs, S.-A. and Agarwal, G. S. (2013). Large enhancement of förster resonance energy transfer on graphene platforms, *ppl. Phys. Lett.* **103**, p. 243112.

Billings, L. (2013). Exotic optics: Metamaterial world, *Nature* **500**, pp. 138–140.

Bludov, Y. V., Ferreira, A., Peres, N. M. R., and Vasilevskiy, M. I. (2013). A primer on surface plasmon-polaritons in graphene, *Int. J. Mod. Phys. B*

27, p. 1341001.

Bludov, Y. V., Smirnova, D. A., Kivshar, Y. S., Peres, N. M. R., and Vasilevskiy, M. I. (2014). Nonlinear te-polarized surface polaritons on graphene, *Phys. Rev. B* **89**, p. 035406.

Boriskina, S. V., Ghasemi, H., and Chen, G. (2013). Plasmonic materials for energy: From physics to applications, *Materials Today* **16**, pp. 375–386.

Brar, V. W., Jang, M. S., Sherrott, M., Kim, S., Lopez, J. J., Kim, L. B., Choi, M., and Atwater, H. (2014). Hybrid surface-phonon-plasmon polariton modes in graphene/monolayer h-bn heterostructures, *Nano Lett.* **14**, pp. 3876–3880.

Brar, V. W., Jang, M. S., Sherrott, M., Lopez, J. J., and Atwater, H. A. (2013). Highly confined tunable mid-infrared plasmonics in graphene nanoresonators, *Nano Lett.* **13**, pp. 2541–2547.

Brolo, A. G. (2012). Plasmonics for future biosensors, *Nature Photonics* **6**, pp. 709–713.

Cai, X., Sushkov, A. B., Jadidi, M. M., Nyakiti, L. O., Myers-Ward, R. L., Gaskill, D. K., Murphy, T. E., Fuhrer, M. S., and Drew, H. D. (2015). Plasmon-enhanced terahertz photodetection in graphene, *Nano Lett.* **15**, pp. 4295–4302.

Cai, Y.-J., Li, M., Ren, X.-F., Zou, C.-L., Xiong, X., Lei, H.-L., Liu, B.-H., Guo, G.-P., and Guo, G.-C. (2014). High-visibility on-chip quantum interference of single surface plasmons, *Phys. Rev. Appl.* **2**, p. 014004.

Caldwell, J. D., Kretinin, A. V., Chen, Y., Giannini, V., Fogler, M. M., Francescato, Y., Ellis, C. T., Tischler, J. G., Woods, C. R., Giles, A. J., Hong, M., Watanabe, K., Taniguchi, T., Maier, S. A., and Novoselov, K. S. (2014). Sub-diffractional volume-confined polaritons in the natural hyperbolic material hexagonal boron nitride, *Nature Communications* **5**, pp. 1–9.

Carbotte, J. P., LeBlanc, J. P. F., and Nicol, E. J. (2012). Emergence of plasmaronic structure in the near-field optical response of graphene, *Phys. Rev. B* **85**, p. 201411(R).

Castro Neto, A. H., Guinea, F., Peres, N. M. R., Novoselov, K. S., and Geim, A. K. (2009). The electronic properties of graphene, *Rev. Mod. Phys.* **81**.

Castro Neto, A. H. and Novoselov, K. (2011). New directions in science and technology: two-dimensional crystals, *Reports on Progress in Physics* **74**, p. 082501.

Chang, D. E., Sørensen, A. S., Hemmer, P. R., and Lukin, M. D. (2006). Quantum optics with surface plasmons, *Phys. Rev. Lett.* **97**, p. 053002.

Chaves, F. A., Jiménez, D., Cummings, A. W., and Roche, S. (2014). Physical model of the contact resistivity of metal-graphene junctions, *Journal of Appl. Phys.* **115**, p. 164513.

Chen, J., Badioli, M., Alonso-González, P., Thongrattanasiri, S., Huth, F., Osmond, J., Spasenović, M., Centeno, A., Pesquera, A., Godignon, P., Elorza, A. Z., Camara, N., de Abajo, F. J. G., Hillenbrand, R., and Koppens, F. H. L. (2012). Optical nano-imaging of gate-tunable graphene plasmons, *Nature* **487**, pp. 77–81.

Chen, P.-Y. and Alù, A. (2011). Atomically thin surface cloak using graphene monolayers, *ACS Nano* **5**, pp. 5855 – 5863.

Chen, Z., Berciaud, S., Nuckolls, C., Heinz, T. F., and Brus, L. E. (2010). Energy transfer from individual semiconductor nanocrystals to graphene, *ACS Nano* **4**, pp. 2964–2968.

Christensen, J., Manjavacas, A., Thongrattanasiri, S., Koppens, F. H. L., and de Abajo, F. J. G. (2012). Graphene plasmon waveguiding and hybridization in individual and paired nanoribbons, *ACS Nano* **6**, 1, pp. 431–440.

Christensen, T., Jauho, A.-P., Wubs, M., and Mortensen, N. A. (2015). Localized plasmons in graphene-coated nanospheres, *Phys. Rev. B* **91**, p. 125414.

Christensen, T., Wang, W., Jauho, A.-P., Wubs, M., and Mortensen, N. A. (2014). Classical and quantum plasmonics in graphene nanodisks: the role of edge states, *Phys. Rev. B* **90**, p. 241414(R).

Constant, T. J., Hornett, S. M., Chang, D. E., and Hendry, E. (2015). All-optical generation of surface plasmons in graphene, *Nat. Phys.* **11**, p. 1.

Cox, J. D. and de Abajo, F. J. G. (2014). Electrically tunable nonlinear plasmonics in graphene nanoislands, *Nature Communications* **5**, 5725.

Cox, J. D. and de Abajo, F. J. G. (2015). Plasmon-enhanced nonlinear wave mixing in nanostructured graphene, *ACS Photonics* **2**, pp. 306–312.

Cox, J. D., Singh, M. R., Gumbs, G., Anton, M. A., and Carreno, F. (2012). Dipole-dipole interaction between a quantum dot and a graphene nanodisk, *Phys. Rev. B* **86**, p. 125452.

Crassee, I., Orlita, M., Potemski, M., Walter, A. L., Ostler, M., Seyller, T., Gaponenko, I., Chen, J., and Kuzmenko, A. B. (2012). Intrinsic terahertz plasmons and magnetoplasmons in large scale monolayer graphene, *Nano Lett.* **12**, pp. 2470–2474.

Crozier, K. B., Zhu, W., Wang, D., Lin, S., Best, M. D., and Camden, J. P. (2014). Plasmonics for surface enhanced raman scattering: Nanoantennas for single molecules, *IEEE Journal of Selected Topics in Quantum Electronics* **20**.

Dai, S., Fei, Z., Ma, Q., Rodin, A. S., Wagner, M., McLeod, A. S., Liu, M. K., Gannett, W., Regan, W., Watanabe, K., Taniguchi, T., Thiemens, M., Dominguez, G., Castro Neto, A. H., Zettl, A., Keilmann, F., Jarillo-Herrero, P., Fogler, M. M., and Basov, D. N. (2014). Tunable phonon polaritons in atomically thin van der waals crystals of boron nitride, *Science* **343**, pp. 1125–1129.

Dai, S., Ma, Q., Zhu, S.-E., Liu, M. K., Andersen, T., Fei, Z., Goldflam, M., Wagner, M., Watanabe, K., Taniguchi, T., Thiemens, M., Keilmann, F., Janssen, G. C. A. M., Jarillo-Herrero, P., Fogler, M. M., and Basov, D. N. (2015). Graphene on hexagonal boron nitride as an agile hyperbolic metamaterial, *Nature Nanotechnology* **10**, pp. 682–686.

de Abajo, F. J. G. (2014). Graphene plasmonics: Challenges and opportunities, *ACS Photonics* **1**, 135-152.

Di Martino, G., Sonnefraud, Y., Tame, M. S., Kéna-Cohen, S., Dieleman, F., Ozdemir, S. K., Kim, M. S., and Maier, S. A. (2014). Observation of quantum interference in the plasmonic hong-ou-mandel effect, *Phys. Rev. Appl.* **1**, p. 034004.

Dionne, J. A. and Atwater, H. A. (2012). Plasmonics: Metal-worthy methods and materials in nanophotonics, *MRS Bulletin* **37**, pp. 717–724.

Ebbesen, T. W., Genet, C., and Bozhevolnyi, S. I. (2008). Surface plasmon circuitry, *Nature* **61**, pp. 44–50.

Ebbesen, T. W., Lezec, H. J., Ghaemi, H. F., Thio, T., and Wolff, P. A. (1998). Extraordinary optical transmission through sub-wavelength hole arrays, *Nature* **391**, pp. 667–669.

Editorial (2012). Surface plasmon resurrection, *Nature Photonics* **6**, p. 707.

Enoch, S. and Bonod, N. (2012). *Plasmonics: From Basics to Advanced Topics* (Springer Series in Optical Sciences, New York).

Fakonas, J. S., Lee, H., Kelaita, Y. A., and Atwater, H. A. (2014). Two-plasmon quantum interference, *Nature Photonics* **8**, pp. 317–320.

Fang, Z., Liu, Z., Wang, Y., Ajayan, P. M., Nordlander, P., and Halas, N. J. (2012a). Graphene-antenna sandwich photodetector, *Nano Lett.* **12**, pp. 3808–3813.

Fang, Z., Thongrattanasiri, S., Schlather, A., Liu, Z., Ma, L., Wang, Y., Ajayan, P. M., Nordlander, P., Halas, N. J., and de Abajo, F. J. G. (2013). Gated tunability and hybridization of localized plasmons in nanostructured graphene, *ACS Nano* **7**, pp. 2388–2395.

Fang, Z., Wang, Y., Liu, Z., Schlather, A., Ajayan, P. M., Koppens, F. H. L., Nordlander, P., and Halas, N. J. (2012b). Plasmon-induced doping of graphene, *ACS Nano* **6**, pp. 10222–10228.

Fang, Z., Wang, Y., Schlather, A. E., Liu, Z., Ajayan, P. M., de Abajo, F. J. G., Nordlander, P., Zhu, X., and Halas, N. J. (2014). Active tunable absorption enhancement with graphene nanodisk arrays, *Nano Lett.* **14**, pp. 299–304.

Fano, U. (1941). The theory of anomalous diffraction gratings and of quasi-stationary waves on metallic surfaces (sommerfeld's waves), *J. Opt. Soc. Am.* **31**, pp. 213–222.

Farhat, M., Guenneau, S., and Bağcı, H. (2011). Exciting graphene surface plasmon polaritons through light and sound interplay, *Phys. Rev. Lett.* **111**, p. 237404.

Fei, Z., Andreev, G. O., Bao, W., Zhang, L. M., McLeod, A. S., Wang, C., Stewart, M. K., Zhao, Z., Dominguez, G., Thiemens, M., Fogler, M. M., Tauber, M. J., Castro Neto, A. H., Lau, C. N., Keilmann, F., and Basov, D. N. (2011). Infrared nanoscopy of dirac plasmons at the graphene–sio2 interface, *Nano Lett.* **11**, pp. 4701–4705.

Fei, Z., Rodin, A. S., Andreev, G. O., Bao, W., McLeod, A. S., Wagner, M., Zhang, L. M., Zhao, Z., Thiemens, M., Dominguez, G., Fogler, M. M., Castro Neto, A. H., Lau, C. N., Keilmann, F., and Basov, D. N. (2012). Gate-tuning of graphene plasmons revealed by infrared nano-imaging, *Nature* **487**, pp. 82–85.

Fei, Z., Rodin, A. S., Gannett, W., Dai, S., Regan, W., Wagner, M., Liu, M. K., McLeod, A. S., Dominguez, G., Thiemens, M., Castro Neto, A. H., Keilmann, F., Zettl, A., Hillenbrand, R., Fogler, M. M., and Basov, D. N. (2013). Electronic and plasmonic phenomena at graphene grain boundaries, *Nature Nanotechnology* **8**, pp. 821 –825.

Gao, W., Shi, G., Jin, Z., Shu, J., Zhang, Q., Vajtai, R., Ajayan, P. M., Kono, J., and Xu, Q. (2013). Excitation and active control of propagating surface

plasmon polaritons in graphene, *Nano Lett.* **13**, pp. 3698–3702.

Garcia, M. A. (2011). Surface plasmons in metallic nanoparticles: fundamentals and applications, *J. Phys. D: Appl. Phys.* **44**, p. 283001.

Gaudreau, L., Tielrooij, K. J., Prawiroatmodjo, G. E. D. K., Osmond, J., de Abajo, F. J. G., and Koppens, F. H. L. (2013). Universal distance-scaling of nonradiative energy transfer to graphene, *Nano Lett.* **13**, pp. 2030–2035.

Geim, A. K. (2009). Graphene: Status and prospects, *Science* **324**, pp. 1530–1534.

Geim, A. K. and Grigorieva, I. V. (2013). Van der waals heterostructures, *Nature* **499**, pp. 419 – 425.

Gilbertson, A. M., Francescato, Y., Roschuk, T., Shautsova, V., Chen, Y., Sidiropoulos, T. P. H., Hong, M., Giannini, V., Maier, S. A., Cohen, L. F., and Oulton, R. F. (2015). Plasmon-induced optical anisotropy in hybrid graphene–metal nanoparticle systems, *Nano Lett.* **15**, pp. 3458–3464.

Gorbach, A. V. (2013). Nonlinear graphene plasmonics: Amplitude equation for surface plasmons, *Phys. Rev. A* **87**, p. 013830.

Green, M. A. and Pillai, S. (2012). Harnessing plasmonics for solar cells, *Nature Photonics* **6**, pp. 130–132.

Grigorenko, A. N., Polini, M., and Novoselov, K. S. (2012). Graphene plasmonics, *Nature Photonics* **6**, pp. 749–758.

Gullans, M., Chang, D. E., Koppens, F. H. L., de Abajo, F. J. G., and Lukin, M. D. (2013). Single-photon nonlinear optics with graphene plasmons, *Phys. Rev. Lett.* **111**, p. 247401.

Gupta, B. D., Srivastava, S. K., and Verma, R. (2015). *Fiber Optic Sensors Based on Plasmonics* (World Scientific, Singapore).

Haes, A. J., Haynes, C. L., McFarland, A. D., Schatz, G. C., Duyne, R. P. V., and Zou, S. (2005). Plasmonic materials for surface-enhanced sensing and spectroscopy, *MRS Bulletin* **30**, pp. 368–375.

Hanson, G. W., Hassani Gangaraj, S. A., Lee, C., Angelakis, D. G., and Tame, M. (2015). Quantum plasmonic excitation in graphene and loss-insensitive propagation, *Phys. Rev. A* **92**, p. 013828.

Heeg, S., Fernandez-Garcia, R., Oikonomou, A., Schedin, F., Narula, R., Maier, S. A., Vijayaraghavan, A., and Reich, S. (2013). Polarized plasmonic enhancement by au nanostructures probed through raman scattering of suspended graphene, *Nano Lett.* **13**, pp. 301–308.

Heeres, R. W., Kouwenhoven, L. P., and Zwiller, V. (2013). Quantum interference in plasmonic circuits, *Nature Nanotechnology* **8**, pp. 719–722.

Hessel, A. and Oliner, A. A. (1965). A new theory of wood's anomalies on optical gratings, *Appl. Optics* **4**, pp. 1275–1297.

Hoggard, A., Wang, L.-Y., Ma, L., Fang, Y., You, G., Olson, J., Liu, Z., Chang, W.-S., Ajayan, P. M., and Link, S. (2013). Using the plasmon linewidth to calculate the time and efficiency of electron transfer between gold nanorods and graphene, *ACS Nano* **7**, pp. 11209–11217.

Huidobro, P. A., Nesterov, M. L., Martín-Moreno, L., and García-Vidal, F. J. (2010). Transformation optics for plasmonics, *Nano Lett.* **10**, pp. 1985–1990.

Huidobro, P. A., Nikitin, A. Y., González-Ballestero, C., Martín-Moreno, L., and García-Vidal, F. J. (2012). Superradiance mediated by graphene surface plasmons, *Phys. Rev. B* **85**, p. 155438.

Hwang, E. H., Sensarma, R., and Sarma, S. D. (2010). Plasmon-phonon coupling in graphene, *Phys. Rev. B* **82**, p. 195406.

Ishikawa, A. and Tanaka, T. (2013). Plasmon hybridization in graphene metamaterials, *Appl. Phys. Lett.* **102**, p. 253110.

Jablan, M., Buljan, H., and Soljačić, M. (2009). Plasmonics in graphene at infrared frequencies, *Phys. Rev. B* **80**, p. 245435.

Jablan, M., Soljačić, M., and Buljan, H. (2013). Plasmons in graphene: Fundamental properties and potential applications, *Proc. IEEE* **101**, pp. 1689 – 1704.

Jacob, Z. (2012). Quantum plasmonics, *MRS Bulletin* **37**, pp. 761–767.

Jacob, Z. (2014). Hyperbolic phonon-polaritons, *Nature Materials* **13**, pp. 1081–1083.

Jacob, Z. and Shalaev, V. M. (2011). Plasmonics goes quantum, *Science* **28**, pp. 463–464.

Ju, L., Geng, B., Horng, J., Girit, C., Martin, M., Hao, Z., Bechtel, H. A., Liang, X., Zettl, A., Shen, Y. R., and Wang, F. (2011). Graphene plasmonics for tunable terahertz metamaterials, *Nature Nanotechnology* **6**, pp. 630–634.

Juan, M. L., Righini, M., and Quidant, R. (2011). Plasmon nano-optical tweezers, *Nature Photonics* **5**, pp. 349–356.

Kabashin, A. V., Evans, P., Pastkovsky, S., Hendren, W., Wurtz, G. A., Atkinson, R., Pollard, R., Podolskiy, V. A., and Zayats, A. V. (2009). Plasmonic nanorod metamaterials for biosensing, *Nature Materials* **8**, pp. 867 – 871.

Kamat, P. V. (2010). Graphene-based nanoarchitectures. anchoring semiconductor and metal nanoparticles on a two-dimensional carbon support, *J. Phys. Chem. Lett.* **1**, pp. 520 – 527.

Kauranen, M. and Zayats, A. V. (2012). Nonlinear plasmonics, *Nature Photonics* **6**, pp. 737–748.

Khurgin, J. B. and Boltasseva, A. (2012). Reflecting upon the losses in plasmonics and metamaterials, *MRS Bulletin* **37**, pp. 768–779.

Kim, J. T., Yu, Y.-J., Choi, H., and Choi, C.-G. (2014). Graphene-based plasmonic photodetector for photonic integrated circuits, *Opt. Express* **22**, pp. 803–808.

Klimov, V. (2014). *Nanoplasmonics* (Pan Stanford).

Kneipp, K. (2007). Surface-enhanced raman scattering, *Phys. Today* **60**, pp. 40–46.

Koch, R. J., Seyller, T., and Schaefer, J. A. (2010). Strong phonon-plasmon coupled modes in the graphene/silicon carbide heterosystem, *Phys. Rev. B* **82**, p. 201413.

Konstantatos, G., Badioli, M., Gaudreau, L., Osmond, J., Bernechea, M., de Arquer, F. P. G., Gatti, F., and Koppens, F. H. L. (2012). Hybrid graphene-quantum dot phototransistors with ultrahigh gain, *Nature Nanotechnology* **7**, pp. 363 – 368.

Koppens, F. H. L., Chang, D. E., and de Abajo, F. J. G. (2011). Graphene

plasmonics: A platform for strong light-matter interactions, *Nano Lett.* **11**, pp. 3370 – 3377.

Koppens, F. H. L., Mueller, T., Avouris, P., Ferrari, A. C., Vitiello, M. S., and Polini, M. (2014). Photodetectors based on graphene, other two-dimensional materials and hybrid systems, *Nature Nanotechnology* **9**, pp. 780–793.

Kravets, V. G., Jalil, R., Kim, Y.-J., Ansell, D., Aznakayeva, D. E., Thackray, B., Britnell, L., Belle, B. D., Withers, F., Radko, I. P., Han, Z., Bozhevolnyi, S. I., Novoselov, K. S., Geim, A. K., and Grigorenko, A. N. (2014). Graphene-protected copper and silver plasmonics, *Scientific Reports* **4**, p. 5517.

Kravets, V. G., Schedin, F., Jalil, R., Britnell, L., Novoselov, K. S., and Grigorenko, A. N. (2012). Surface hydrogenation and optics of a graphene sheet transferred onto a plasmonic nanoarray, *The Journal of Physical Chemistry C* **116**, pp. 3882–3887.

Kretinin, A. V., Cao, Y., Tu, J. S., Yu, G. L., Jalil, R., Novoselov, K. S., Haigh, S. J., Gholinia, A., Mishchenko, A., Lozada, M., Georgiou, T., Woods, C. R., Withers, F., Blake, P., Eda, G., Wirsig, A., Hucho, C., Watanabe, K., Taniguchi, T., Geim, A. K., and Gorbachev, R. V. (2014). Electronic properties of graphene encapsulated with different two-dimensional atomic crystals, *Nano Lett.* **14**, pp. 3270 – 3276.

Kretschmann, E. and Raether, H. (1968). Radiative decay of nonradiative surface plasmon excited by light, *Z. Naturf. A* **23**, pp. 2135–2136.

Kumar, A., Low, T., Fung, K. H., Avouris, P., and Fang, N. X. (2015). Tunable light-matter interaction and the role of hyperbolicity in graphene-hbn system, *Nano Lett.* **15**, pp. 3172–3180.

Lee, S. H., Choi, M., Kim, T.-T., Lee, S., Liu, M., Yin, X., Choi, H. K., Lee, S. S., Choi, C.-G., Choi, S.-Y., Zhang, X., and Min, B. (2012). Switching terahertz waves with gate-controlled active graphene metamaterials, *Nature Materials* **11**, pp. 936 – 941.

Li, Z. Q., Henriksen, E. A., Jiang, Z., Hao, Z., Martin, M. C., Kim, P., Stormer, H. L., and Basov, D. N. (2008). Dirac charge dynamics in graphene by infrared spectroscopy, *Nature Phys.* **4**, pp. 532–535.

Lim, D.-K., Barhoumi, A., Wylie, R. G., Reznor, G., Langer, R. S., and Kohane, D. S. (2013). Enhanced photothermal effect of plasmonic nanoparticles coated with reduced graphene oxide, *Nano Lett.* **13**, pp. 4075–4079.

Ling, X., Xie, L., Fang, Y., Xu, H., Zhang, H., Kong, J., Dresselhaus, M. S., Zhang, J., and Liu, Z. (2010). Can graphene be used as a substrate for raman enhancement? *Nano Lett.* **10**, pp. 553–561.

Liu, C.-Y., Liang, K.-C., Chen, W., hao Tu, C., Liu, C.-P., and Tzeng, Y. (2011a). Plasmonic coupling of silver nanoparticles covered by hydrogen-terminated graphene for surface-enhanced raman spectroscopy, *Opt. Express* **19**.

Liu, F., Qian, C., and Chong, Y. D. (2015a). Directional excitation of graphene surface plasmons, *Opt. Express* **23**, pp. 2383–2391.

Liu, H., Sun, S., Wu, L., and Bai, P. (2014). Optical near-field enhancement with graphene bowtie antennas, *Plasmonics* **9**, pp. 845–850.

Liu, P. Q., Valmorra, F., Maissen, C., and Faist, J. (2015b). Electrically tunable graphene anti-dot array terahertz plasmonic crystals exhibiting multi-band resonances, *Optica* **2**, pp. 135 – 140.

Liu, Y., Cheng, R., Liao, L., Zhou, H., Bai, J., Liu, G., Liu, L., Huang, Y., and Duan, X. (2011b). Plasmon resonance enhanced multicolour photodetection by graphene, *Nature Communications* **2**, 579.

Liua, Y. and Zhang, X. (2011). Metamaterials: a new frontier of science and technology, *Chem. Soc. Rev.* **40**, pp. 2494–2507.

Llatser, I., Kremers, C., Cabellos-Aparicio, A., Jornet, J. M., Alarcón, E., and Chigrin, D. N. (2012). Graphene-based nano-patch antenna for terahertz radiation, *Photonics and Nanostructures - Fundamentals and Applications* **10**, pp. 353–358.

Low, T. and Avouris, P. (2014). Graphene plasmonics for terahertz to mid-infrared applications, *ACS Nano* **8**, pp. 1086–1101.

Low, T., Guinea, F., Yan, H., Xia, F., and Avouris, P. (2014a). Novel mid-infrared plasmonic properties of bilayer graphene, *Phys. Rev. Lett.* **112**, p. 116801.

Low, T., Roldán, R., Wang, H., Xia, F., Avouris, P., Moreno, L. M., and Guinea, F. (2014b). Plasmons and screening in monolayer and multilayer black phosphorus, *Phys. Rev. Lett.* **113**, p. 106802.

Luo, X., Qiu, T., Lu, W., and Ni, Z. (2013). Plasmons in graphene: Recent progress and applications, *Materials Science and Engineering R* **74**, pp. 351 – 376.

Luxmoore, I. J., Gan, C. H., Liu, P. Q., Valmorra, F., Li, P., Faist, J., and Nash, G. R. (2014). Strong coupling in the far-infrared between graphene plasmons and the surface optical phonons of silicon dioxide, *ACS Photonics* **1**, p. 1151.

Ma, R.-M., Oulton, R. F., Sorger, V. J., and Zhang, X. (2013). Plasmon lasers: coherent light source at molecular scales, *Laser Photon. Rev.* **7**, pp. 1–21.

MacDonald, K. F., Sámson, Z. L., Stockman, M. I., and Zheludev, N. I. (2009). Ultrafast active plasmonics, *Nature Photonics* **3**, pp. 55–58.

Maier, S. A. (2007). *Plasmonics: Fundamentals and Applications* (Springer, New York).

Manjavacas, A., Marchesin, F., Thongrattanasiri, S., Koval, P., Nordlander, P., Sánchez-Portal, D., and de Abajo, F. J. G. (2013). Tunable molecular plasmons in polycyclic aromatic hydrocarbons, *ACS Nano* **7**, pp. 3635–3643.

Manjavacas, A., Nordlander, P., and de Abajo, F. J. G. (2012a). Plasmon blockade in nanostructured graphene, *ACS Nano* **6**, pp. 1724 – 1731.

Manjavacas, A., Thongrattanasiri, S., Chang, D. E., and de Abajo, F. J. G. (2012b). Temporal quantum control with graphene, *New J. Phys.* **14**, p. 123020.

Manjavacas, A., Thongrattanasiri, S., Greffet, J.-J., and de Abajo, F. J. G. (2014). Graphene optical-to-thermal converter, *Appl. Phys. Lett.* **105**, p. 211102.

Manzoni, M. T., Silveiro, I., de Abajo, F. J. G., and Chang, D. E. (201). Second-order quantum nonlinear optical processes in graphene nanostructures, *New J. Phys.* **17**, p. 083031.

Maradudin, A. A., Barnes, W. L., and Sambles, J. R. (eds.) (2014). *Modern*

Plasmonics (Elsevier).

Martín-Moreno, L., García-Vidal, F. J., Lezec, H. J., Pellerin, K. M., Thio, T., Pendry, J. B., and Ebbesen, T. W. (2001). Theory of extraordinary optical transmission through subwavelength hole arrays, *Phys. Rev. Lett.* **86**, pp. 1114–1117.

Mikhailov, S. A. and Ziegler, K. (2007). New electromagnetic mode in graphene, *Phys. Rev. Lett.* **99**, p. 016803.

Mishchenko, A., Tu, J. S., Cao, Y., Gorbachev, R. V., Wallbank, J. R., Greenaway, M., Morozov, V. E., Morozov, S. V., Zhu, M. J., Wong, S. L., Withers, F., Woods, C. R., Kim, Y.-J., Watanabe, K., Taniguchi, T., Vdovin, E. E., Makarovsky, O., Fromhold, T. M., Falko, V. I., Geim, A. K., Eaves, L., and Novoselov, K. S. (2014). Twist-controlled resonant tunnelling in graphene-boron nitride-graphene heterostructures, *Nature Nanotechnology* **9**, pp. 808–813.

Mittleman, D. M. (2013). Frontiers in terahertz sources and plasmonics, *Nature Photonics* **7**, pp. 666–669.

Moriya, R., Yamaguchi, T., Inoue, Y., Sata, Y., Morikawa, S., Masubuchi, S., and Machida, T. (2015). Influence of the density of states of graphene on the transport properties of graphene/mos2/metal vertical field-effect transistors, *Appl. Phys. Lett.* **106**, p. 223103.

Nene, P., Strait, J. H., Chan, W.-M., Manolatou, C., Kevek, J. W., Tiwari, S., McEuen, P. L., and Rana, F. (2014). Coupling of plasmon modes in graphene microstructures, *Appl. Phys. Lett.* **105**, p. 143108.

Nikitin, A. Y., Low, T., and Martin-Moreno, L. (2014). Anomalous reflection phase of graphene plasmons and its influence on resonators, *Phys. Rev. B* **90**, p. 041407.

Niu, J., Shin, Y. J., Son, J., Lee, Y., Ahn, J.-H., and Yang, H. (2012). Shifting of surface plasmon resonance due to electromagnetic coupling between graphene and au nanoparticles, *Opt. Express* **20**, pp. 19690 – 19696.

Novoselov, K. S. and Castro Neto, A. H. (2012). Two-dimensional crystals-based heterostructures: materials with tailored properties, *Physica Scripta* **2012**, p. 014006.

Novoselov, K. S., Geim, A. K., Morozov, S. V., Jiang, D., Zhang, Y., Dubonos, S. V., Grigorieva, I. V., and Firsov, A. A. (2004). Electric field effect in atomically thin carbon films, *Science* **306**, pp. 666–669.

Otto, A. (1968). Excitation of nonradiative surface plasma waves in silver by the method of frustrated total reflection, *Z. Phys.* **216**, pp. 398–410.

Ozbay, E. (2006). Plasmonics: Merging photonics and electronics at nanoscale dimensions, *Science* **311**, pp. 189–193.

Pelton, M., Aizpurua, J., and Bryant, G. (2008). Metal-nanoparticle plasmonics, *Laser & Photon. Rev.* **2**, pp. 136–159.

Pelton, M. and Bryant, G. W. (2013). *Introduction to Metal-Nanoparticle Plasmonics*, 1st edn. (John Wiley & Sons, Inc, New Jersey).

Peres, N. M. R., Bludov, Y. V., Santos, J. E., Jauho, A.-P., and Vasilevskiy, M. I. (2014). Optical bistability of graphene in the terahertz range, *Phys. Rev. B* **90**, p. 125425.

Peres, N. M. R., Ferreira, A., Bludov, Y. V., and Vasilevskiy, M. I. (2012). Light scattering by a medium with a spatially modulated optical conductivity: the case of graphene, *J. Phys.: Condens. Matter* **24**, p. 245303.

Polanco, J., Fitzgerald, R. M., and Maradudin, A. A. (2013). Scattering of surface plasmon polaritons by one-dimensional surface defects, *Phys. Rev. B* **87**, p. 155417.

Politano, A. and Chiarello, G. (2014). Plasmon modes in graphene: status and prospect, *Nanoscale* **6**, pp. 10927–10940.

Powell, C. J. and Swan, J. B. (1959). Origin of the characteristic electron energy losses in aluminum, *Phys. Rev.* **115**, p. 869.

Quidant, R. (2012). Plasmonic tweezers—the strength of surface plasmons, *MRS Bulletin* **37**, pp. 739–744.

Rayleigh, L. (1907). On the dynamical theory of gratings, *Proc. R. Soc. Lond. A* **79**, pp. 399–416.

Reece, P. J. (2008). Plasmonics: Finer optical tweezers, *Nature Photonics* **2**, pp. 333–334.

Ritchie, R. H. (1957). Plasma losses by fast electrons in thin films, *Phys. Rev.* **106**, p. 874.

Ritchie, R. H., Arakawa, E. T., Cowan, J. J., and Hamm, R. N. (1968). Surface-plasmon resonance effect in grating diffraction, *Phys. Rev. Lett.* **21**, pp. 1530–1533.

Rodrigo, D., Limaj, O., DavideJanner, Etezadi, D., de Abajo, F. J. G., Pruneri, V., and Altug, H. (2015). Mid-infrared plasmonic biosensing with graphene, *Science* **349**, 6244, pp. 165–168.

Sambles, J. R., Bradberya, G. W., and Yang, F. (1991). Optical excitation of surface plasmons: An introduction, *Contemporary Physics* **32**, pp. 173–183.

Sánchez-Gil, J. A. and Maradudin, A. A. (1999). Near-field and far-field scattering of surface plasmon polaritons by one-dimensional surface defects, *Phys. Rev. B* **60**, pp. 8359–8367.

Santos, J. E., Vasilevskiy, M. I., Peres, N. M. R., Smirnov, G., and Bludov, Y. V. (2014). Renormalization of nanoparticle polarizability in the vicinity of a graphene-covered interface, *Phys. Rev. B* **90**, p. 235420.

Sarid, D. and Challener, W. (2010). *Modern Introduction to Surface Plasmons: Theory, Mathematica Modeling, and Applications* (Cambridge University Press, Cambridge).

Schiefele, J., Pedrós, J., Sols, F., Calle, F., and Guinea, F. (2013). Coupling light into graphene plasmons through surface acoustic waves, *Phys. Rev. Lett.* **111**, p. 237405.

Schlücker, S. (2014). Surface-enhanced raman spectroscopy: Concepts and chemical applications, *Angew. Chem. Int. Ed.* **53**, pp. 4756 – 4795.

Sensale-Rodriguez, B., Yan, R., Zhu, M., Jena, D., Liu, L., and Grace Xing, H. (2012). Efficient terahertz electro-absorption modulation employing graphene plasmonic structures, *Appl. Phys. Lett.* **101**, 26, p. 261115.

Sharma, B., Frontiera, R. R., Henry, A.-I., Ringe, E., and Duyne, R. P. V. (2012). Sers: Materials, applications, and the future, *Materials Today* **15**, pp. 16 –

25.

Slipchenko, T. M., Nesterov, M. L., Martin-Moreno, L., and Nikitin, A. Y. (2013). Analytical solution for the diffraction of an electromagnetic wave by a graphene grating, *J. Opt.* **15**, p. 114008.

Sommerfeld, A. (1899). Über die fortpflanzung elektrodynamischer wellen an längs eines drahtes, *Ann. der Physik und Chemie* **67**, pp. 233–290.

Sorger, C., Preu, S., Schmidt, J., Winnerl, S., Bludov, Y. V., Peres, N. M. R., Vasilevskiy, M. I., and Weber, H. B. (2015). Terahertz response of patterned epitaxial graphene, *New J. of Phys.* **17**, p. 053045.

Sorger, V. J., Oulton, R. F., Ma, R.-M., and Zhang, X. (2012). Toward integrated plasmonic circuits, *MRS Bulletin* **37**, pp. 728–738.

Stauber, T. (2014). Plasmonics in dirac systems: from graphene to topological insulators, *J. Phys.: Condens. Matter* **26**, p. 123201.

Stiles, P. L., Dieringer, J. A., Shah, N. C., and Duyne, R. P. V. (2008). Surface-enhanced raman spectroscopy, *Annu. Rev. Anal. Chem.* **1**, pp. 601 – 626.

Stockman, M. I. (2011). Nanoplasmonics: The physics behind the applications, *Phys. Today* **64**, pp. 39–44.

Strait, J. H., Nene, P., Chan, W.-M., Manolatou, C., Tiwari, S., Rana, F., Kevek, J. W., and McEuen, P. L. (2013). Confined plasmons in graphene microstructures: Experiments and theory, *Phys. Rev. B* **87**, p. 241410.

Sun, S., Gao, L., Liu, Y., and Sun, J. (2011). Assembly of cdse nanoparticles on graphene for low-temperature fabrication of quantum dot sensitized solar cell, *Appl. Phys. Lett.* **98**.

Tame, M. S., McEnery, K. R., Ozdemir, S. K., Lee, J., Maier, S. A., and Kim, M. S. (2013). Quantum plasmonics, *Nature Phys.* **9**, pp. 329–340.

Tassin, P., Koschny, T., and Soukoulis, C. M. (2013). Graphene for terahertz applications, *Science* **341**, pp. 620–621.

Temnov, V. V. (2012). Ultrafast acousto-magneto-plasmonics, *Nature Photonics* **6**, pp. 728–736.

Thongrattanasiri, S. and de Abajo, F. J. G. (2013). Optical field enhancement by strong plasmon interaction in graphene nanostructures, *Phys. Rev. Lett.* **110**, p. 187401.

Thongrattanasiri, S., Koppens, F. H. L., and de Abajo, F. J. G. (2012a). Complete optical absorption in periodically patterned graphene, *Phys. Rev. Lett.* **108**, p. 047401.

Thongrattanasiri, S., Manjavacas, A., and de Abajo, F. J. G. (2012b). Quantum finite-size effects in graphene plasmons, *ACS Nano* **6**, pp. 1766–1775.

Tielrooij, K. J., Orona, L., Ferrier, A., Badioli, M., Navickaite, G., Coop, S., Nanot, S., Kalinic, B., Cesca, T., Gaudreau, L., Ma, Q., Centeno, A., Pesquera, A., Zurutuza, A., de Riedmatten, H., Goldner, P., de Abajo, F. J. G., Jarillo-Herrero, P., and Koppens, F. H. L. (2015). Electrical control of optical emitter relaxation pathways enabled by graphene, *Nature Phys.* **11**, pp. 281 – 287.

Tomadin, A., Guinea, F., and Polini, M. (2014). Generation and morphing of plasmons in graphene superlattices, *Phys. Rev. B* **89**, p. 224512.

Toropov, A. A. and Shubina, T. V. (2015). *Plasmonic Effects in Metal-*

Semiconductor Nanostructures (Oxford).

Torre, I., Tomadin, A., Krahne, R., Pellegrini, V., and Polini, M. (2015). Electrical plasmon detection in graphene waveguides, *Phys. Rev. B* **91**, p. 081402(R).

Turbadar, T. (1959). Complete absorption of light by thin metal films, *Proceedings of the Physical Society* **73**, p. 40.

Urich, A., Pospischil, A., Furchi, M. M., Dietze, D., Unterrainer, K., and Mueller, T. (2012). Silver nanoisland enhanced raman interaction in graphene, *Appl. Phys. Lett.* **101**, p. 153113.

Vakil, A. and Engheta, N. (2011). Transformation optics using graphene, *Science* **332**, pp. 1291 – 1294.

van Hulst, N. F. (2012). Nanophotonics: Plasmon quantum limit exposed, *Nature Nanotechnology* **7**, pp. 775 – 777.

Vasić, B., Isić, G., and Gajić, R. (2013). Localized surface plasmon resonances in graphene ribbon arrays for sensing of dielectric environment at infrared frequencies, *J. Appl. Phys.* **113**, p. 013110.

Velizhanin, K. A. (2015). Geometric universality of plasmon modes in graphene nanoribbon arrays, *Phys. Rev. B* **91**, p. 125429.

Velizhanin, K. A. and Efimov, A. (2011). Probing plasmons in graphene by resonance energy transfer, *Phys. Rev. B* **84**, p. 085401.

Vo-Dinh, T., Fales, A. M., Griffin, G. D., Khoury, C. G., Liu, Y., Ngo, H., Norton, S. J., Register, J. K., Wang, H.-N., and Yuan, H. (2013). Plasmonic nanoprobes: from chemical sensing to medical diagnostics and therapy, *Nanoscale* **5**, pp. 10127–10140.

Wang, P., Liang, O., Zhang, W., Schroeder, T., and Xie, Y.-H. (2013). Ultrasensitive graphene-plasmonic hybrid platform for label-free detection, *Advanced Materials* **25**, pp. 4918 – 4924.

Wang, P., Zhang, W., Liang, O., Pantoja, M., Katzer, J., Schroeder, T., and Xie, Y.-H. (2012). Giant optical response from graphene–plasmonic system, *ACS Nano* **6**, pp. 6244–6249.

Wang, W., Christensen, T., Jauho, A.-P., Thygesen, K. S., Wubs, M., and Mortensen, N. A. (2015). Plasmonic eigenmodes in individual and bow-tie graphene nanotriangles, *Scientific Reports* **5**, 9535.

Weber, M. L. and Willets, K. A. (2012). Nanoscale studies of plasmonic hot spots using super-resolution optical imaging, *MRS Bulletin* **37**, pp. 745–751.

Willets, K. A. and Duyne, R. P. V. (2007). Localized surface plasmon resonance spectroscopy and sensing, *Annu. Rev. Phys. Chem.* **58**, pp. 267–297.

Woessner, A., Lundeberg, M. B., Gao, Y., Principi, A., Alonso-González, P., Carrega, M., Watanabe, K., Taniguchi, T., Vignale, G., Polini, M., Hone, J., Hillenbrand, R., and Koppens, F. H. L. (2015). Highly confined low-loss plasmons in graphene-boron nitride heterostructures, *Nature Materials* **14**, pp. 421–425.

Wood, R. W. (1902). On a remarkable case of uneven distribution of light in a diffraction grating spectrum, *Philosophical Magazine* **4**, pp. 396–402.

Wu, J., Zhou, C., Yu, J., Cao, H., Li, S., and Jia, W. (2014a). Design of infrared surface plasmon resonance sensors based on graphene ribbon arrays, *Optics and Laser Technology* **59**, pp. 99 – 103.

Wu, J.-Y., Gumbsand, G., and Lin, M.-F. (2014b). Combined effect of stacking and magnetic field on plasmon excitations in bilayer graphene, *Phys. Rev. B* **89**, p. 165407.

Wu, L., Chu, H. S., Koh, W. S., and Li, E. P. (2010). Highly sensitive graphene biosensors based on surface plasmon resonance, *Opt. Express* **18**, pp. 14395 – 14400.

Xiao, S., Zhu, X., Li, B.-H., and Mortensen, N. A. (2016). Graphene-plasmon polaritons: From fundamental properties to potential applications, *Front. Phys.* **11**, p. 117801.

Xu, G., Liu, J., Wang, Q., Hui, R., Chen, Z., Maroni, V. A., and Wu, J. (2012a). Graphene: Plasmonic graphene transparent conductors, *Adv. Mater.* **24**, pp. 1521 – 4095.

Xu, W., Ling, X., Xiao, J., Dresselhaus, M. S., Kong, J., Xu, H., Liu, Z., and Zhang, J. (2012b). Surface enhanced raman spectroscopy on a flat graphene surface, *Proceedings of the National Academy of Sciences* **109**, 24, pp. 9281–9286.

Yamaguchi, T., Moriya, R., Inoue, Y., Morikawa, S., Masubuchi, S., Watanabe, K., Taniguchi, T., and Machida, T. (2014). Tunneling transport in a few monolayer-thick ws2/graphene heterojunction, *Appl. Phys. Lett.* **105**, p. 223109.

Yan, H., Li, X., Chandra, B., Tulevski, G., Wu, Y., Freitag, M., Zhu, W., Avouris, P., and Xia, F. (2012a). Tunable infrared plasmonic devices using graphene/insulator stacks, *Nature Nanotechnology* **7**, pp. 330–334.

Yan, H., Li, Z., Li, X., Zhu, W., Avouris, P., and Xia, F. (2012b). Infrared spectroscopy of tunable dirac terahertz magneto-plasmons in graphene, *Nano Lett.* **12**, pp. 3766–3771.

Yan, H., Low, T., Zhu, W., Wu, Y., Freitag, M., Li, X., Guinea, F., Avouris, P., and Xia, F. (2013). Damping pathways of mid-infrared plasmons in graphene nanostructures, *Nat. Photonics* **7**, pp. 394–399.

Yan, H., Xia, F., Li, Z., and Avouris, P. (2012c). Plasmonics of coupled graphene micro-structures, *New J. Phys.* **14**, p. 125001.

Yao, Y., Kats, M. A., Genevet, P., Yu, N., Song, Y., Kong, J., and Capasso, F. (2013). Broad electrical tuning of graphene-loaded plasmonic antennas, *Nano Lett.* **13**, pp. 1257–1264.

Yeung, K. Y. M., Chee, J., Yoon, H., Song, Y., Kong, J., and Ham, D. (2014). Far-infrared graphene plasmonic crystals for plasmonic band engineering, *Nano Lett.* **14**, pp. 2479–2484.

Yin, P. T., Kim, T.-H., Choi, J.-W., and Lee, K.-B. (2013). Prospects for graphene-nanoparticle-based hybrid sensors, *Phys. Chem. Chem. Phys.* **15**, pp. 12785 – 12799.

Yusoff, A. R. B. M. (2014). *Graphene Optoelectronics: Synthesis, Characterization, Properties, and Applications* (Wiley).

Zeng, S., Hu, S., Xia, J., Anderson, T., Dinh, X.-Q., Meng, X.-M., Coquet, P., and Yong, K.-T. (2015). Graphene-mos_2 hybrid nanostructures enhanced surface plasmon resonance biosensors, *Sensors and Actuators B: Chemical* **207**, pp. 801–810.

Zenneck, J. (1907). Uber die fortpflanztmg ebener elektro-magnetischer wellen langs einer ebenen leiterflache und ihre beziehung zur drahtlosen telegraphie, *Annalen der Physik* **23**, pp. 846–866.

Zhan, T., Han, D., Hu, X., Liu, X., Chui, S.-T., and Zi, J. (2014). Tunable terahertz radiation from graphene induced by moving electrons, *Phys. Rev. B* **89**, p. 245434.

Zhang, J., Sun, Y., Xu, B., Zhang, H., Gao, Y., Zhang, H., and Song, D. (2013). A novel surface plasmon resonance biosensor based on graphene oxide decorated with gold nanorod-antibody conjugates for determination of transferrin, *Biosensors and Bioelectronics* **45**, pp. 230 – 236.

Zhang, J., Xiao, S., Wubs, M., and Mortensen, N. A. (2011). Surface plasmon wave adapter designed with transformation optics, *ACS Nano* **5**, pp. 4359–4364.

Zhang, Q., Li, X., Hossain, M. M., Xue, Y., Zhang, J., Song, J., Liu, J., Turner, M. D., Fan, S., Bao, Q., and Gu, M. (2014). Graphene surface plasmons at the near-infrared optical regime, *Scientific Reports* **4**, p. 6559.

Zhao, Y., Chen, G., Du, Y., Xu, J., Wu, S., Qu, Y., and Zhu, Y. (2014). Plasmonic-enhanced raman scattering of graphene on growth substrates and its application in sers, *Nanoscale* **6**, pp. 13754 – 13760.

Zhao, Y., Hu, X., Chen, G., Zhang, X., Tan, Z., Chen, J., Ruoff, R. S., Zhu, Y., and Lu, Y. (2013). Infrared biosensors based on graphene plasmonics: modeling, *Phys. Chem. Chem. Phys.* **15**, pp. 17118 – 17125.

Zheng, Y. B., Kiraly, B., Weiss, P. S., and Huang, T. J. (2012). Molecular plasmonics for biology and nanomedicine, *Nanomedicine* **7**, pp. 751 – 770.

Zhu, J., Liu, Q. H., and Lin, T. (2013a). Manipulating light absorption of graphene using plasmonic nanoparticles, *Nanoscale* **5**, pp. 7785 – 7789.

Zhu, X., Shi, L., Schmidt, M. S., Boisen, A., Hansen, O., Zi, J., Xiao, S., and Mortensen, N. A. (2013b). Enhanced light–matter interactions in graphene-covered gold nanovoid arrays, *Nano Lett.* **13**, pp. 4690–4696.

Zhu, X., Wang, W., Yan, W., Larsen, M. B., Bøggild, P., Pedersen, T. G., Xiao, S., Zi, J., and Mortensen, N. A. (2014). Plasmon-phonon coupling in large-area graphene dot and antidot arrays fabricated by nanosphere lithography, *Nano Lett.* **14**, pp. 2907 – 2913.

Zhu, X., Yan, W., Uhd Jepsen, P., Hansen, O., Asger Mortensen, N., and Xiao, S. (2013c). Experimental observation of plasmons in a graphene monolayer resting on a two-dimensional subwavelength silicon grating, *Appl. Phys. Lett.* **102**, p. 131101.